



PRE-STRETCH FILMS

SPECIFICATION	UNIT	VALUE	VALUE	VALUE	VALUE
Type		Hand / Machine	Hand / Machine	Hand / Machine	Hand / Machine
Width	Mm	390-500	390-500	390-500	390-500
Thickness	Micron	8	7	6	5
Color		Clear / Any Color	Clear / Any Color	Clear / Any Color	Clear / Any Color
Process		Cast/Blown	Cast/Blown	Cast/Blown	Cast/Blown
Tensile MD	Kg/cm ²	380	330	280	230
Tensile TD	Kg/cm ²	220	170	120	70
Tear Strength MD	Elemendorf	380	330	280	230
Tear Strength TD	Elemendorf	990	940	890	840
Residue Pre-Stretch	%	<20	<20	<20	<20
Core	mm	38/51/76	38/51/76	38/51/76	38/51/76
Edge Fold	5 mm	Optional	Optional	Optional	Optional

HYDERABAD | ABU DHABI | AURANGABAD

| E: info@mauryansindustries.com, mauryansindustries@gmail.com |