



# SILAGE WRAP

SPECIFICATION	UNIT	VALUE
Type		Agri Stretch
Width	Mm	750/500/250
Thickness	Micron	25
Weight Per Roll	Kg	25/21/10.3
Meters Meters Roll	Kg	1500/1800/1800
UV Protection	Months	6-12
Kly Levels		Max 150
Color		White / Black / Green
Elongation MD	%	650 – 850
Elongation TD	%	800 – 900
Tensile MD	Kg/cm <sup>2</sup>	350 – 480
Tensile TD	Kg/cm <sup>2</sup>	250 – 300
Tear Strength MD	Elemendorf	400 - 500
Tear Strength TD	Elemendorf	750 - 1200

## STORAGE / HANDLING

- Keep Silage rolls away from heat
- Keep packed rolls away from rain
- Storage Temperature – Max 32 deg. Cent.
- Rolls should be used on First In First out Basis (FIFO)
- Do not roll the wrapped rolls as damage may occur
- Store wrapped bales on film tale ends only
- Inspect the bales regularly and repair holes if any caused by rodent or other animals
- Store unused rolls in dry area and cool area
- Do not allow film or bales to come in contact with any chemicals as this may cause premature breakdown of the film
- Max pre-stretch 70-% only
- UV protection as below under standard conditions from the date of wrapping provided the bales should be stored under conditions as mentioned above
  - 120 KLY – 9 -12 months
  - 140 KLY – 6 -9 months
  - 160 KLY – 4 -6 months

HYDERABAD | ABU DHABI | AURANGABAD

| E: info@mauryansindustries.com, mauryansindustries@gmail.com |